

METALLIC STEARATES OVERVIEW OF PROPERTIES

TYPICAL PROPERTIES	TOTAL ASH % (CORRECTED FOR MOISTURE)	TOTAL ASH	MOISTURE %	FREE FATTY ACID %	SOFTENING POINT °C	APPARENT DENSITY (LB/FT ³)	MEAN PARTICLE SIZE (MICRONS)	FINENESS % THRU (MESH)
Aluminum Stearate								
Mathe® Aluminum Stearate No. 9	**	10.3	1	5	170	20		100 (200)
Calcium Stearate								
COAD® 10	10.3	10.0	2.5	0.2	155	18	11	99 (325)
COAD® 10 VG	10.3	10.0	2.5	0.2	155	18	11	99 (325)
COAD® 10B	10.3	10.0	2.5	0.2	155	16	7	99 (400)
COAD® 10C	10.3	10.0	2.5	0.2	155	17	8.5	100 (325)
COAD® 10F	10.3	10.0	2.5	0.2	155	18	17	99 (200)
COAD® 10LD	10.3	10.0	2.5	0.5	155	24	**	95 (20)
COAD® 10LD VG	10.3	10.0	2.5	0.2	155	24	**	95 (20)
COAD® 13D	9.8	9.5	2.5	0.5	155	18	11	99 (325)
COAD® 13D VG	10.2	9.9	2.5	0.5	155	18	11	99(325)
COAD® 13F	9.8	9.5	2.5	0.5	155	18	17	99 (200)
COAD® 13F VG	10.2	9.9	2.5	0.5	155	18	17	99 (200)
COAD® 13LD	9.8	9.5	2.5	0.5	155	20	**	95 (20)
COAD® 13LD VG	10.2	9.9	2.5	0.5	155	20	**	95 (20)
LIGAFOOD CPR-2-K-MB	**	9.5	<4.0	<1	**	**	7	99 (325)
Lithium Stearate								
Mathe® Lithium Stearate	**	5.4	0.5	0.5	212	12	**	100 (200)
Magnesium Stearate								
COAD® 40	**	7.7	4	3	**	24	**	90 (20)
COAD® 41	**	8.2	4	1.5	**	**	**	90 (20)
LIGAFOOD MF-2-K-MB	**	7.5	<4	<2	**	**	9	99 (200)
Potassium Stearate								
Mathe® Potassium Stearate	**	13.9	0.5	1	235	48	**	
Sodium Stearate								
Mathe® Sodium Stearate	**	10.3	1.7	0.5	220	28	**	100 (100)
Zinc Stearate								
COAD® 20	15.3	15.3	0.2	0.2	120	18	11	99 (325)
COAD® 21 (Clear Melt)	13.6	13.6	0.2	0.7	120	18	11	99 (325)
COAD® 23 (Polymer Grade)	13.6	13.6	0.2	0.2	120	18	11	99 (325)
COAD® 23 VG	13.6	13.6	0.2	0.2	120	18	11	99 (325)
COAD® 25	13.6	13.6	0.2	0.2	120	16	7	99 (400)
COAD® 27D	13.6	13.6	0.2	0.2	120	18	11	99 (325)
COAD® 27F	13.6	13.5	0.5	0.2	120	20	18	99 (200)
COAD® 30 Prill	15.3	15.3	0.2	0.2	122	42	**	99 (20)
COAD® 31 Prill (Clear Melt)	13.6	13.6	0.2	0.5	122	40	**	99 (20)
COAD® 33 Prill	13.6	13.6	0.2	0.2	122	40	**	99 (20)
COAD® 33 VG	13.6	13.6	0.2	0.3	122	40	**	99 (20)
COAD® DISPERSO II	15.3	15.3	0.2	0.2	120	18	11	99 (325)
COAD® HA	17	16.9	0.7	0.2	120	18	7	99 (400)
PALMSTAR ZPR-2-V	**	13.5	<1.0	<1.5	**	**	13.5	99 (325)

METALLIC STEARATES OVERVIEW OF PROPERTIES

STORAGE AND HANDLING RECOMMENDATIONS

- Storage:** Store at ambient temperatures away from sources of heat or from places of extreme moisture.
- Fire:** Use water from a safe distance, preferably with a fog nozzle.
- Handling:** Avoid contact with skin or eyes. Safety goggles are recommended.
- Spills:** Clean up immediately. Sweep up and discard in a closed container.
- Disposal:** Consult Federal, State and Local regulations. Consult the telephone book or EPA for list of approved disposal companies.
- Other:** See MSDS for COAD[®], MATHE[®], LIGAFOOD[®] or PALMSTAR[®] Metallic Stearates for additional health, safety and environmental information.

PACKAGING

Metallic Stearates are packaged in various sized multiwall bags and supersacks, unitized on non-returnable wooden pallets. Please contact your Norac sales representative to discuss your special packaging requirements.

CORPORATE HEADQUARTERS

Norac Additives LLC
813 Town Center Drive
Pomona, CA 91767
USA

MANUFACTURING FACILITY

Norac Additives LLC
360 Phillips 311 Road
Helena, AR 72342
USA

CUSTOMER SERVICE

Telephone: 1-888-786-6722
Fax: 1-870-572-4650

"The information contained in this bulletin is based on information received of our staff and of others and is presented in good faith and with every belief in its accuracy. Due to the extensive technology involved in its usage, the manufacturing in no way guarantees such information, nor does he make any recommendations as to its use in the infringement of any patent. The information contained in this bulletin supersedes and replaces all information contained in all previous bulletins. Seller makes no warranty of any kind, expressed or implied, except that the good sold hereunder shall meet specifications of the buyer. After the good sale accepted by the buyer within the time specified the buyer assumes all risk and liability for damages resulting from the use of the good. Whether used by the buyer singly or in combination with other products or if sold by buyer to third persons either in its original form or if repackaged by the buyer and then sold to third persons."
