





COAD® LM Calcium Stearate Disperso

DESCRIPTION

COAD® LM Calcium Stearate Disperso is specifically formulated to disperse readily in aqueous systems with gentle stirring. The fine particle size aids in handling and ensures even distribution of the stearate.

TYPICAL PROPERTIES

Total Ash, %	9.8
Moisture, %	2.0
Free Fatty Acid, %	2.0
Soluble Salts, %	Nil
Softening Point, C	130
Apparent Density, lbs/ft3	20
Mean Particle Size, microns	11
Top Size %98, microns	35
% Thru 325 Mesh	99
Appearance	Free flowing white powder

APPLICATIONS

• Rubber Processing: COAD® LM Calcium Stearate Disperso is used on uncured rubber stocks to prevent adhesion. Uniform coatings are deposited on slabs or extruded forms from aqueous dispersions in dip tanks or baths.

Norac Additives, LLC 813 Towne Center Drive Pomona, CA 91767

P: 888.786.6722 F: 870.572.4650

Noracadditives.com

COAD® LM Calcium Stearate Disperso TECHNICAL DATA SHEET

Product Bulletin: 1/28/18

ADDITIONAL INFORMATION

Other

 See SDS for COAD® LM Calcium Stearate Disperso for additional health, safety, and environmental information.

Packaging

COAD® Calcium Stearates are packaged in various sized multiwall bags and supersacks, unitized on non-returnable wooden pallets. Please contact your Norac sales representative to discuss your special packaging requirements.

Norac Additives, LLC 813 Towne Center Drive Pomona, CA 91767 P: 888.786.6722

P: 888.786.6722 F: 870.572.4650

Noracadditives.com

[&]quot;The information contained in this bulletin is based on information received of our staff and of others and is presented in good faith and with every belief in its accuracy. Due to the extensive technology involved in its usage, the manufacturer in no way guarantees such information, nor does he make any recommendations as to its use in the infringement of any patent. The information contained in this bulletin supersedes and replaces all information contained in all previous bulletins. Seller makes no warranty of any kind, expressed or implied, except that the goods sold hereunder shall meet specifications of the buyer. After the good sale accepted by the buyer within the time specified the buyer assumes all risk and liability for damages resulting from the use of the goods. Whether used by the buyer singly or in combination with other products or if sold by buyer to third persons either in its original form or if repackaged by the buyer and then sold to third persons."