

## **NORAC<sup>®</sup>** **TPSA**

### **DESCRIPTION**

NORAC<sup>®</sup> TPSA is a triple press stearic acid which can be used as an external lubricant in rigid PVC formulations. It also can be used in filled flexible PVC applications as both an internal and external lubricant. In some mixed metal stabilized PVC formulations, NORAC<sup>®</sup> TPSA acts as a dispersing agent for the stabilizer.

### **TYPICAL PROPERTIES**

Appearance	Off-white powder or beads
Iodine Value	0.5 max
Acid Number	206–212
Lovibond (5.25) Red	0.3 max

### **APPLICATIONS**

- **PVC Rigid Profile & Sheet Extrusion**
- **PVC Flexible Film & Sheet**
- **PVC Wire & Cable**
- **PVC Roofing Membrane**
- **PVC Flooring & Cove Base**

### **USAGE LEVEL RECOMMENDATION**

- 0.1 – 0.5 phr

## ADDITIONAL INFORMATION

- Other – See SDS for NORAC® TPSA for additional health, safety, and environmental information.
- Packaging – NORAC® TPSA is packaged in various sized multiwall bags and supersacks, unitized on non-returnable wooden pallets. Please contact your Norac sales representative to discuss your special packaging requirements.